

## Xylex\* Resin X8409

### Europe-Africa-Middle East: COMMERCIAL

PC + Polyester, Injection Molding or Injection/Extrusion Blow Molding Grade, Chemical Resistance and Transparency

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	UNIT	STANDARD
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	610	kgf/cm <sup>2</sup>	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	560	kgf/cm <sup>2</sup>	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	92	%	ASTM D 638
Tensile Modulus, 50 mm/min	22700	kgf/cm <sup>2</sup>	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	950	kgf/cm <sup>2</sup>	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	22600	kgf/cm <sup>2</sup>	ASTM D 790
Tensile Stress, yield, 50 mm/min	60	MPa	ISO 527
Tensile Stress, break, 50 mm/min	60	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.8	%	ISO 527
Tensile Strain, break, 50 mm/min	117	%	ISO 527
Tensile Modulus, 1 mm/min	2180	MPa	ISO 527
Flexural Stress, break, 2 mm/min	89	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, notched, 23°C	87	cm-kgf/cm	ASTM D 256
Instrumented Impact Total Energy, 23°C	734	cm-kgf	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	10	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -10°C	8	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	123	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	116	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	104	°C	ASTM D 648

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.

3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

4) Own measurement according to UL.

Source, GMD, Last Update: 09/12/2005

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA. All information, recommendation or advice given by SABIC Innovative Plastics IP BV, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC INNOVATIVE PLASTICS HOLDING BV or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

\* Xylex is a trademark of SABIC INNOVATIVE PLASTICS HOLDING BV

© 1997-2008 SABIC INNOVATIVE PLASTICS HOLDING BV. All rights reserved

## Xylex\* Resin X8409

### Europe-Africa-Middle East: COMMERCIAL

TYPICAL PROPERTIES <sup>1</sup>	TYPICAL VALUE	UNIT	STANDARD
<b>THERMAL</b>			
CTE, -40°C to 40°C, flow	1.04E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	1.04E-04	1/°C	ASTM E 831
Thermal Conductivity	0.23	W/m-°C	ISO 8302
CTE, 23°C to 60°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	7.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/120	123	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	102	°C	ISO 75/Ae
<b>PHYSICAL</b>			
Specific Gravity	1.2	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 - 0.8	%	SABIC Method
Mold Shrinkage, xflow, 3.2 mm	0.5 - 0.8	%	SABIC Method
Density	1.2	g/cm <sup>3</sup>	ISO 1183
Melt Volume Rate, MVR at 265°C/2.16 kg	3	cm <sup>3</sup> /10 min	ISO 1133
<b>OPTICAL</b>			
Light Transmission	88	%	ASTM D 1003
Haze	1.5	%	ASTM D 1003
Refractive Index	1.576	-	ASTM D 542

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.  
All properties, except the melt volume rate are measured on injection moulded samples.  
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.  
3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.  
4) Own measurement according to UL.

Source, GMD, Last Update: 09/12/2005

**PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA** All information, recommendation or advice given by SABIC INNOVATIVE PLASTICS HOLDING BV, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC INNOVATIVE PLASTICS HOLDING BV or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

\* Xylex is a trademark of SABIC INNOVATIVE PLASTICS HOLDING BV

© 1997-2008 SABIC Innovative Plastics IP BV. All rights reserved

## Xylex\* Resin X8409

### Europe-Africa-Middle East: COMMERCIAL

PROCESSING PARAMETERS	TYPICAL VALUE	UNIT
<b>Extrusion Blow Molding</b>		
Drying Temperature	75 - 90	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	24	hrs
Maximum Moisture Content	0.01 - 0.02	%
Melt Temperature (Parison)	250 - 270	°C
Barrel - Zone 1 Temperature	235 - 260	°C
Barrel - Zone 2 Temperature	235 - 260	°C
Barrel - Zone 3 Temperature	235 - 260	°C
Barrel - Zone 4 Temperature	235 - 260	°C
Adapter - Zone 5 Temperature	235 - 260	°C
Head - Zone 6 - Top Temperature	240 - 270	°C
Head - Zone 7 - Middle Temperature	240 - 270	°C
Head - Zone 7 - Bottom Temperature	240 - 270	°C
Mold Temperature	30 - 75	°C

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity.  
All properties, except the melt volume rate are measured on injection moulded samples.  
All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.  
3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.  
4) Own measurement according to UL.

Source, GMD, Last Update: 09/12/2005

**PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA** All information, recommendation or advice given by SABIC INNOVATIVE PLASTICS HOLDING BV, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC INNOVATIVE PLASTICS HOLDING BV, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC INNOVATIVE PLASTICS HOLDING BV or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

\* Xylex is a trademark of SABIC INNOVATIVE PLASTICS HOLDING BV

© 1997-2008 SABIC Innovative Plastics IP BV. All rights reserved